



AS Schöler + Bolte GmbH

Normenvergleich/ Comparison of standards/ Comparaison des normes

| AS | Wst.-Nr. | AISI | AFNOR | BSI | DIN | GOST | JIS | MNC | UNE | UNI | UNS |
|----------|----------|------|---------------|--------|--------------------|-------------|--------------|------|--------|------------------|---------|
| 304 | 1.4301 | 304 | Z7 CN 18 09 | 304S11 | X5 CrNi 18 10 | 08Ch18N10 | SUS 304 | 2333 | F.3504 | X5 CrNi 18 10 | S 30400 |
| 309 | 1.4828 | 309 | Z17 CNS 20 12 | 309S24 | X15 CrNiSi 20 12 | 20Ch20N14S2 | SUH 309 | | F.3312 | X16 CrNi 23 14 | S 30900 |
| 310 | 1.4845 | 310S | Z12 CN 25 20 | 310S16 | X15 CrNi 25 21 | 20Ch23N18 | SUH310S | 2361 | F.331 | X6CrNi 25 20 | S 31008 |
| 314 | 1.4841 | 314 | Z15 CNS 25 20 | 314S25 | X15 CrNiSi 25 20 | 20Ch25N20S2 | SUH 310 | | F.3310 | X16 CrNiSi 25 20 | S 31400 |
| 253MA | 1.4883 | | | | X8 CrNiSiN 21 11 | | | 2368 | | | |
| 330 | 1.4864 | 330 | Z20 NCS 33 16 | NA 17 | X12 NiCrSi 36 16 | | SUH 330 | | F.3313 | | N 08330 |
| 601 | 2.4851 | | | | | | NCF 601 | | | | |
| 602CA | 2.4633 | | | | NiCr 25 FeAl | | | | | | |
| 625 | 2.4856 | | NC 22 DNB | | NiCr 22 Mo 9 Nb | | | | | | N 06625 |
| 800H/ HT | 1.4876 | B163 | | | X10 NiCrAlTi 32 20 | | NCF 800 (TP) | | F.3314 | | |

| | |
|----------|---|
| AS | AS-Bezeichnung, AS-nomenclature |
| WSt.-Nr. | Deutsche Werkstoff-Nummer |
| AISI | American Iron and Steel Institute |
| AFNOR | Association Française de Normalisation |
| BSI | British Standards Institution |
| DIN | Deutsches Institut für Normung |
| GOST | Committee for Standards, Measures and Measuring Instruments (GUS) |
| JIS | Japanese Institute for Standardization |
| MNC | Metallnormcentralen (Sweden) |
| UNE | Instituto Nacional de Racionalización y Normalización (Spain) |
| UNI | Ente Nazionale Italiano de Unificazione |
| UNS | Unified Numbering System |